



Covac Ltd, Unit 7, St. John's Business Park, Rugby Road, Lutterworth, Leicestershire, LE17 4HB.
Tel: +44 (0)1455 556631 • Fax: +44 (0)1455 550872 • Email: info@covac.co.uk • Web: www.covac.co.uk

COMPLETION REPORT

Client : **XXXXXXXXXX Hospital**

Project Brief : **The Internal Relining of 2 No. Hotwell Tanks**

Site Address : **UK**

Site Contact : **XXXXXXXXXXXX**

System Spec : **3M Scotchkote™ 175**
Formerly known as COPON Hycote 175

Film Thickness : **600 Microns**

Completion Date : **August 2002**

Compiled By : **Craig Phillips**

Covac Ref : **194**



Company registration number 03213628
Registered in England VAT number 670 635334
© Copyright 2010 COVAC Ltd. All rights reserved.





The main boiler house, hotwell tank and towers ring hotwell tank were previously internally coated with a blue epoxy coating which had now come to the end of its useful life.







Both tanks were internally dry grit blast cleaned to a minimum SA 2.5 BS7079 Part A1 1989 i.e. complete removal of all existing coating and corrosion.



Two coats of COPON Hycote 175 high temperature epoxy was then applied by brush and roller to achieve a total nominal dry film thickness of 600 Mcirons.





Following a minimum 7 day curing period the tanks were re-filled and brought back up to temperature.