



Covac Ltd, Unit 7, St. John's Business Park, Rugby Road, Lutterworth, Leicestershire, LE17 4HB.
Tel: +44 (0)1455 556631 • Fax: +44 (0)1455 550872 • Email: Info@covac.co.uk • Web: www.covac.co.uk

COMPLETION REPORT

Client : **XXXXXXXXX University**

Project Brief : **The Internal Relining of 2 No. Hotwell Tanks
Chemical Engineering Dept**

Site Contact : **XXXXXXXXX**

System Spec : **COPON Hycote 175**

Film Thickness : **600 Microns**

Completion Date : **August 2003**

Compiled By : **Craig Phillips**

Covac Ref : **261**



Company registration number: 03213678
Registered in England VAT number: 670 635334
© Copyright 2010 COVAC Ltd. All rights reserved





The above and following photographs show the internal condition of the tank prior to refurbishment.







All internal surfaces were DRY Grit Blast Cleaned to a minimum SA2.5 Swedish Standard i.e. Complete removal of all rust, paint & foreign matter.





COPON Hycote 175 High Temperature Epoxy was then applied in 2 Coats by hand application to achieve a nominal dry film thickness of 600 Microns.



