



Covac Ltd, Unit 7, St. John's Business Park, Rugby Road, Lutterworth, Leicestershire, LE17 4HB.
Tel: +44 (0)1455 556631 • Fax: +44 (0)1455 550872 • Email: info@covac.co.uk • Web: www.covac.co.uk

COMPLETION REPORT

Client : **Drinks Manufacturer**

Project Brief : **The Internal Refurbishment of 1 No. Process Water Truff Tank**

Site Address : **Cheshire**

Site Contact : **XXXXXXXXXX**

System Spec : **3M Scotchkote™ 165PW**
(Formerly Known as COPON Hycote 165PW)

Film Thickness : **1000 Microns**

Covac Supervisor : **Timothy Ray**

Completion Date : **October 2003**

Compiled By : **Craig Phillips**

Covac Ref : **242**

CONTENTS

- 1. Summary of Works**
- 2. Photographs Detailing Strategic Stages of the Contract.**
- 3. Dry Film Thickness Readings Taken Utilizing an Elcometer Microprocessor.**
- 4. Ten Year 'Single Source Responsibility' Guarantee.**




The above photographs show the internal condition of the tank prior to refurbishment.






All internal surfaces were dry grit blast cleaned to a minimum SA 2.5 standard ie, all existing coatings and corrosion were completely removed.





All weld seams, joints and flanges etc, were firstly stripe coated prior to a full coat application.



COPON Hycote 165PW was then spray applied through two component hot plural feed airless spray equipment to achieve a final nominal dry film thickness of 1000 microns (see dft readings).





